



US006387453B1

(12) **United States Patent**
Brinker et al.

(10) **Patent No.:** **US 6,387,453 B1**
(45) Date of Patent: **May 14, 2002**

(54) **METHOD FOR MAKING
 SURFACTANT-TEMPLATED THIN FILMS**

(75) **Inventors:** **C. Jeffrey Brinker**, Albuquerque, NM
 (US); **Yunfeng Lu**, San Jose, CA (US);
Hongyou Fan, Albuquerque, NM (US)

(73) **Assignee:** **Sandia Corporation**, Albuquerque, NM
 (US)

(*) **Notice:** Subject to any disclaimer, the term of this
 patent is extended or adjusted under 35
 U.S.C. 154(b) by 0 days.

(21) **Appl. No.:** **09/517,873**

(22) **Filed:** **Mar. 2, 2000**

(51) **Int. Cl.⁷** **B05D 3/02; B05D 3/10;**
B05D 1/02; B05D 3/12; B05D 1/18

(52) **U.S. Cl.** **427/387; 427/240; 427/245;**
427/346; 427/376.2; 427/377; 427/397.7;
427/421; 427/430.1

(58) **Field of Search** **427/245, 240,**
427/346, 377, 376.2, 397.7, 387, 421, 430.1

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,595,715 A * 1/1997 Roth 423/328.1
 5,858,457 A * 1/1999 Brinker et al. 427/162
 6,177,534 B1 * 1/2001 Antonucci et al. 528/26

OTHER PUBLICATIONS

Fowler et al., "Synthesis and Characterization of Ordered
 Organo-Silica-Surfactant Mesophases with Functionalized
 MCM-41-Type Architecture", CHEM. COMMUN., 1997,
 p. 1769-1770.*

Sellinger et al., "Continuous Self-Assembly of Organic-In-
 organic Nanocomposite Coatings that Mimic Nacre",
 NATURE, vol. 394, Jul. 1998, pp. 256-260.*

Burkett, S., Sims, S., and Mann, S., "Synthesis of Hybrid
 Inorganic-organic Mesoporous Silica by Co-condensation
 of Siloxane and Organosiloxane Precursors," Chem. Com-
 mun., 1996, 11, 1367-1368.

Fowler, C., Burkett, S., and Mann, S., "Synthesis and
 Characterization of Ordered Organo-silica-surfactant
 Mesophases with Functionalized MCM-41-type Architec-
 ture," Chem. Commun., 1997, 1769-1770.

Lim, M., Blandford, C., and Stein, A., "Synthesis and Char-
 acterization of a Reactive Vinyl-functionalized MCM-41:
 Probing the Internal Pore Structure by a Bromination Reac-
 tion," J. Am. Chem. Soc., 1997, 119, 4090-4091.

Feng, X., Fryxell, G., Wang, L., Kim, A. Liu, J., and
 Kemner, K., "Functionalized Monolayers on Ordered Meso-
 porous Supports," Science, 1997, 276, 923-926.

Sellinger, A., Weiss, P., Nguyen, A., Lu, Y., Assink, R.,
 Gong, W., and Brinker, C., "Continuous Self-assembly of
 Organic-inorganic Nanocomposite Coatings that Mimic
 Nacre," Nature, 1998, 394, 256-260.

Moroi, Y., Motomura, K., and Matuura, R., "The Critical
 Micelle Concentration of Sodium Dodecyl Sulfate-Bivalent
 Metal Dodecyl Sulfate Mixtures in Aqueous Solutions,"
 1974, 46, 1, 111-117, Journal of Colloid and Interface
 Science.

* cited by examiner

Primary Examiner—Michael Barr

(74) *Attorney, Agent, or Firm*—Elmer A. Klavetter

(57) **ABSTRACT**

An evaporation-induced self-assembly method to prepare a
 porous, surfactant-templated, thin film by mixing a silica
 sol, a solvent, a surfactant, and an interstitial compound,
 evaporating a portion of the solvent to form a liquid,
 crystalline thin film mesophase material, and then removal
 of the surfactant template. Coating onto a substrate produces
 a thin film with the interstitial compound either covalently
 bonded to the internal surfaces of the ordered or disordered
 mesostructure framework or physically entrapped within the
 ordered or disordered mesostructured framework. Particles
 can be formed by aerosol processing or spray drying rather
 than coating onto a substrate. The selection of the interstitial
 compound provides a means for developing thin films for
 applications including membranes, sensors, low dielectric
 constant films, photonic materials and optical hosts.

21 Claims, 7 Drawing Sheets

